

# IDENDEN SPRAYABLE VAPOUR BARRIER COATING ET-150

Idenden Sprayable Vapour Barrier Coating ET-150 is ideal for applications in the thermal insulation industry as a vapour barrier coating for internal and external insulated piping, equipment and air conditioning ducting. It is also suitable as an asbestos encapsulant. Idenden Sprayable Vapour Barrier Coating ET-150 is a high quality polymer emulsion available in white, grey and black. It is easily applied by spray or brush to provide a durable and flexible, water-resistant finish over a wide service temperature range. Idenden Sprayable Vapour Barrier Coating ET-150 has Class 0 compliance and therefore dries to form a flame resistant finish.

**Features**

- Easily applied by spray or brush
- Dries to form a flexible, durable and water-resistant finish
- Solvent free
- Non-marine pollutant
- Class 0 compliance

**Product Characteristics**

<b>Colour</b>	White, black and grey Non-standard colours are available on request
<b>Form</b>	Thixotropic liquid
<b>Weight per litre</b>	1.4 kg 60% solids
<b>Composition</b>	Co-polymer emulsion
<b>Packaging</b>	10 litre polybuckets
<b>Shelf life/storage</b>	At least 12 months from date of manufacture when stored unopened in a cool, dry place within the temperature range +5°C to +25°C and out of direct sunlight. PROTECT FROM FROST

**Typical Performance Data (approx.)**

<b>Drying time</b>	<i>Touch:</i> 2 hours <i>Through:</i> 24 hours
<b>Service temperature</b>	-29°C to +82°C
<b>Application temperature</b>	Above +5°C (External work should not be completed in poor drying conditions or when rain is imminent).
<b>Reaction to fire</b>	<i>Wet:</i> Non-flammable <i>Dry:</i> Class 0 compliance: Independently tested to BS 476 Part 6 and 7 – class 1
<b>Coverage</b>	0.5 – 4.0 sqm/litre per coat (dependant on substrate and performance requirements)

**Water vapour permeance** (0.034 g/sMN) (0.6 perms) at 1mm dry film thickness (ASTM E96 Method A)

**Solvent for cleaning up** *Wet:* Water  
*Dry:* White spirit

**Directions for use****IMPORTANT**

Before embarking on any work involving Idenden Sprayable Vapour Barrier Coating ET-150, the separate Safety Data Sheet should be carefully studied by those carrying out the work.

1. Surfaces should be clean, dry and free from dust, oil, grease and any loose materials.
2. A) PIPE OR DUCT INSULATION  
Using spray or brush, apply Idenden Sprayable Vapour Barrier Coating ET-150 to the entire surface. Embed a reinforcement membrane such as scrim canvas or glass cloth into the wet coat taking care to smooth out all wrinkles. Overlap all seams and joints by 50 mm. Apply a second coat of Idenden Sprayable Vapour Barrier Coating ET-150 after the first is touch dry and within 24 hours.  
  
B) ASBESTOS ENCAPSULATION  
Only sound asbestos should be coated, and surface preparation should be in line with local authority regulations. Apply Idenden PVA Sealer 30-17 as per the instructions on the Product Data Sheet. Using spray or brush, apply Idenden Sprayable Vapour Barrier Coating ET-150 to the entire surface ensuring any small crevices are properly coated. Apply a second coat of Idenden Sprayable Vapour Barrier Coating ET-150 the following day. Areas subject to mechanical damage such as joints may require additional protection with a reinforcement membrane.
3. COVERAGE  
Optimal performance is achieved by applying this minimum coverage rate:  
  
INTERNAL - Apply two coats, each at a rate of 2 sqm/l to achieve a dry film thickness of 0.5 mm.  
  
EXTERNAL - Apply two coats, the first at a rate of 1 sqm/l and the second at a rate of 1.5 sqm/l to achieve a dry film thickness of 0.8 mm.
4. SPRAY INSTRUCTIONS  
Idenden Sprayable Vapour Barrier Coating ET-150 may be sprayed with a variety of airless spray systems. However, the following system has proved successful:  
  
Pump: Airlessco 5100 / Graco Ultra 1095  
Fluid Hose: 9mm diameter up to 15m hose length  
Gun: Airlessco 007  
Tip: 0.017-0.021 Reverse-a-quick nozzle

This Product Data Sheet covers just one of a large range of products supplied by Bostik Findley Limited. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This Product Data Sheet supersedes all previous technical information on this product, and users of it are cautioned to ensure that it is the current issue. Destroy all previous Product Data Sheets, and if any doubt, contact Bostik Findley Limited, quoting the code number in the top right hand corner on the front of this document. This leaflet is for general guidance only and may contain inappropriate information under particular conditions of use. The company cannot accept any responsibility for loss or damage that may result from the use of this information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm the suitability of this product by their own tests.

5. DRYNESS TEST

A dried film can be tested by gently rubbing the coating with a clean damp rag. If no colour is removed, the film has dried effectively and will exhibit good water resistance. When used externally, adequate temporary protection/tenting should be provided as Idenden Sprayable Vapour Barrier Coating ET-150 dries. This will prevent damage from precipitation and aid good film formation and through drying.

6. Clean application equipment and spillage immediately with cold water.

NOTE: Use of a different colour of Idenden Sprayable Vapour Barrier Coating ET-150 is recommended for the second coat to ensure complete coverage is achieved.

Do not allow standing water to form on Idenden Sprayable Vapour Barrier Coating ET-150 coated surfaces by ensuring the upper surface is shaped to make a 15° slope prior to application of coating.

**Precautions in Use**

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate health and safety data sheet for Idenden Sprayable Vapour Barrier Coating ET-150.

---

This Product Data Sheet covers just one of a large range of products supplied by Bostik Findley Limited. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This Product Data Sheet supersedes all previous technical information on this product, and users of it are cautioned to ensure that it is the current issue. Destroy all previous Product Data Sheets, and if any doubt, contact Bostik Findley Limited, quoting the code number in the top right hand corner on the front of this document. This leaflet is for general guidance only and may contain inappropriate information under particular conditions of use. The company cannot accept any responsibility for loss or damage that may result from the use of this information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm the suitability of this product by their own tests.

Bostik Findley Limited, Common Road, Stafford, ST16 3EH, England    Tel: +44 (0)1785 272727    Fax: +44 (0)1785 257898    [www.bostikfindley.co.uk](http://www.bostikfindley.co.uk)